



- 1 Surface finish  
SEDA | TENSEO | PUROTEC
- 2 Wear layer of approx. 3.6 mm  
from selected solid wood
- 3 Core layer of quarter sawn European  
conifer wood
- 4 Plywood inserts at both ends (water-  
resistant) with integrated locking tongue
- 5 Ends with hydrophobic impregnation,  
prevents humidity and reduces creaking  
of wood
- 6 2 mm spruce bottom  
vener sanded

PRODUCT	DIMENSIONS	PACKAGING	WEIGHT/PACK	PACKAGING	WEIGHT/PAL.
WOODflor 222   2400 NOVOLOC® 5G	14 x 222 x 2400 mm	6 pieces/pack = 3.197 m <sup>2</sup>	approx. 28 kg	32 packs/pallet = 102.304 m <sup>2</sup>	approx. 890 kg
WOODflor 222   2200 NOVOLOC® 5G	14 x 222 x 2200 mm	6 pieces/pack = 2.930 m <sup>2</sup>	approx. 26 kg	32 packs/pallet = 93.773 m <sup>2</sup>	approx. 830 kg
WOODflor 182 NOVOLOC® 5G	14 x 182 x 2200 mm	6 pieces/pack = 2.402 m <sup>2</sup>	approx. 20 kg	40 packs/pallet = 96.080 m <sup>2</sup>	approx. 800 kg
WOODflor 140 NOVOLOC® 5G	14 x 140 x 2200 mm	6 pieces/pack = 1.848 m <sup>2</sup>	approx. 15 kg	56 packs/pallet = 103.488 m <sup>2</sup>	approx. 840 kg
WOODflor 182 3-strip NOVOLOC® 5G	14 x 182 x 2200 mm	6 pieces/pack = 2.402 m <sup>2</sup>	approx. 20 kg	40 packs/pallet = 96.080 m <sup>2</sup>	approx. 800 kg

### PRODUCT FEATURES

Multilayer parquet with NOVOLOC® 5G or tongue and groove system for floating or glue-down installation on standard-compliant subfloors, according to EN 13489

Wear layer	1-strip from selected solid wood with a wear layer of approx. 3.6 mm	
Core layer	Central European conifer wood in spruce or pine with plywood end caps	
Back layer	spruce veneer	
Moisture content	delivered with a moisture content of 7 % +/- 2 %. according to EN 13489:2021	
Gluing	ULEF Amino-glue (Ultra-Low Emitting Formaldehyde), formaldehyde-exempt from declaration	
Surface	Naturally oiled, oxidative drying surface:  Further details on surface treatments can be found in the respective data sheets.	Varnished surfaces: UV-lacquers from Bona, Sweden:  <b>TENSEO CLASSICO</b> (gloss level 29±5 °GU) <b>TENSEO X-MATT</b> with excimer technology (gloss level 9±2 °GU) <b>PUROTEC</b> with excimer technology (gloss level 5 ±1°GU)
Installation	Glueless, floating or glue-down installation with NOVOLOC® 5G interlocking system	
Underfloor heating	suitable, R <sub>f</sub> = 0.101 m <sup>2</sup> K/W, please pay attention to our specifications for the installation above underfloor heatings	
Fields of use	Floors and walls, living and object area (meet the highest class C according to ÖN C2354)	
Room climate	Room temperature should be kept at a constant of 18–24°C and the relative humidity between 30% und 65%! This generally requires an appropriate air humidification in the heating season. We therefor recommend cold humidifiers with an integrated sterilization system. The installation of a Fidbox records your climate above and under your parquet floor, reports deviations from the optimum climate and can be conveniently monitored by mobile app.	

Reaction to fire	floating installation: Dfl-s1   500 kg/m   14 mm glue-down installation: Cfl - s1   500 kg/m   14 mm
Formaldehyde emission	E1
PCP emission	<5 × 10 <sup>-6</sup>
Thermal conductivity	0.14 W/mK
Biological durability	Class 1
Release of other dangerous substances	complies with EU-ECOLABEL, German AgBB-scheme, French. A+, Belgian VOC Regulation, LEED v4, BREEAM Gen.Level

